ALPHA® HI-POXY 9490TM

DESCRIPTION

ALPHA HI-POXY 9490TM is one component epoxy to cure in low-temperature range. It is designed for bonding heat sensitive devices.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

FEATURES AND BENEFITS

- One component
- Halogen-free
- Fast cure at low-temperature
- Excellent adhesion
- Excellent workability

PRODUCT INFORMATION

Chemical Type:	Epoxy
Appearance:	Light brown paste
Curing Method:	Heat cure
Typical Applications:	Adhesive
Packing:	ALPHA HI-POXY 9490TM product can be filled in various specified syringes per customer request.

TECHNICAL DATA

Category	Results
Typical Properties of Uncured Material	
Viscosity (Malcom PC-10A, 30rpm, @25 °C, cps)	10,000 to 25,000
Thixotropic Index	4.0 to 6.0
Specific Gravity	1.1 to 1.3
Pot Life @ 25 °C, days	3
Shelf Life @ -20 °C, months	6

Recommended Cure Condition

≥ 5 minutes @ 80 °C (Convection oven)

Cure Condition for Samsung Electronics

≥ 200 minutes @ 90 °C (Hot-bar)

Optimal cure conditions will depend on curing equipment.

Cure conditions may be dissimilar based on customers working process and application requirements.

Use recommended cure condition as general guideline. Other cure conditions may yield satisfactory results.

Category	Results
Physical Properties of Cured Material	
Hardness (Shore D)	60 to 70
Glass Transition Temperature (Tg), TMA	43(±5)
Coefficient of Thermal Expansion, TMA $^{a}_{1}$,<Tg,ppm $^{a}_{2}$,<Tg,ppm	 60(±10) 190(±20)
Corrosion 95hours @ 40 °C, 95%RH	None
Moisture Absorption, wt% 24hours @ water/25 °C	≤1.0
Insulation Resistance 95hours @ 40 °C, 95%RH	≥1 x 10^{12}

ALPHA HI-POXY 9490TM is NOT fixed specification for mass production. Specific details may alter due to additional modification.

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

STORAGE

Optimal Storage: -20 °C

Store in unopened container, freezer at below -20 °C.

Storage greater than -20 °C can adversely affect product properties.

Pot life of material is valid when stored at suggested storage condition. Inappropriate storage may degrade the performance of the product during dispensing and final cured properties.

Transfer product from dry ice to freezer with **NO** delays.

DO NOT open the cap before the product is sufficiently thawed.

Material must be thawed at room temperature for 2hours.

DO NOT re-freeze. Product should not be re-frozen, once thawed from room temperature.

DO NOT return product to original container.

CONTACT INFORMATION

www.macdermidalpha.com

North America	**Europe**	**Asia**
140 Centennial Avenue Piscataway, NJ 08854 1.800.367.5460	Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400	14 Joo Koon Crescent, Singapore 629014 65.6430.0700

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE . Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.